

Cork natural panel LISOFLEX ASSO "SC"

	CORK THERMAL TRASMITTANCE	CORK THERMAL RESISTANCE
Thickness (mm.)	U Wm ² K	R m ² K/W
20	1,574	0,4651163
30	1,152	0,6976744
40	0,908	0,9302326
50	0,75	1,1627907
60	0,638	1,3953488
70	0,556	1,627907
80	0,492	1,8604651
90	0,441	2,0930233
100	0,4	2,0930233
110	0,366	2,5581395
120	0,337	2,7906977

PANEL DIMENSION 103X60 cm. TICKNESS; 4/6/10/15/20/30 mm. DENSITY 250-300 Kg/mc ca. THERMAL CONDUCTIVITY 0,052 W/mK RESISTANCE RATE TO VAPOUR DIFFU-SION $\mu = 10$ WATER ABSORPTION IN IMMERSION AT CONSTANT TEMPERATURE After 3 days 19,4% vol. After 28 days 34,4% vol. WATER ABSORPTION IN FLOATING CON-DITION AT CONSTANT TEMPERATURE After 3 days 1 1,9% vol. After 28 days 28,8% vol. FOR ALTERATION DIMENSIONAL SHIFTING FROM DRY TO WET ENVIRO-MENT (35% Ur 90%) +11,5%. DIMENSIONAL **ALTERATION** FOR SHIFTING FROM WET TO DRY ENVIRO-MENT (35%- Ur 90%) -1 1 ,7%. DIMENSIONAL VARIATION The coefficient of linear expansion is 62 x 10-6 mm/"C. Under environmental conditions of 20°C and Ur 65% and undergoing conditions of 20°C and Ur 95%, the agglomerate will suffer a maximum variation of 0.60% in 12 days, tending to stabilization. At the end of the 12th day, it will tend to

At the end of the 12th day, it will tend to recover, decreasing to approx. 0.26% of linear

expansion until the initial conditions are restored.

SOUND ABSORPTION

The sound propagation speed through LIS KORK is 450-500 m/s.

Airplane noises can be reduced by 32-35 dB with a cork thickness of 3 cm.

Pattering noises can be reduced as follows:

- 20 dB in the low frequency

- 40 dB in the midle frequency

- 30 dB in the high frequency

Reverberation:

- in empty room di 200 mc. 0,5 sec.

- in empty room di 500 mc. 0,6 sec.

ELECTROSTATIC BEHAVIOUR

Cork is antistatic.

COMPRESSION TENSION WITH 10% SHORTENING

0,22 N/mm2

RESISTANCE TO VERTICAL TENSILE STRESS On the dishes surface 0,16 N/mm2 SPECIFIC HEAT (THERMAL MASS CAPACITY)

1900 - 2100 J/Kg K (a 20°)

RESISTANCE TO DAMPNESS

Its permeability to water vapour at 23°C with Ur 85% 0.21 g/m h mm Hg.

RESISTANCE TO FIRE

Weakly inflammable and weakly smoky. It is very important to point out this physical characteristic regarding the reaction of LIS compressed natural cork to fire! Of course, fire never destroys cork, and on the occasion of tests carried out all over the world results have always been the same: cork has a surface with a very low or almost null fire propagation speed.

REACTION TO FIRE (ITALY)

Class 2; self-extinguishing

"TI VE AFNOR" PROVISIONS Class M 2 = without fire

Class F 2 = without smoke

ANTI-VIBRATION

In order to limit and reduce the vibrations caused by industrial machines or moving machines, it is recommended to use a cork with the highest density (300 Kg/m³) because it can better stand high pressure without suffering from deformations. STABILITY TO AGEING:

Practically UNLIMITED, even under very severe conditions.

RESISTANCE TO CHEMICALS:

good water-tightness, good resistance to hydrochloric, sulphuric and lactic acid (10%); good resistance to concentrated citric acid, to benzene and ethyl alcohol; light degradation with acetic acid, 10% with ammonia, ethyl acetate and trichloroethylene.

Degradable from the sodium carbonate used at 10%.

RESISTANCE TO BIOLOGICAL AGENTS: cryptogamic development after 28 days (in conformity with test AFNOR x 41-504). RESISTANCE TO COMPRESSION:

7,0 Kg/cm² ca.

POSSIBILITY OF ATTACK BY INSECTS OR RODENTS: NON EDIBLE

L.I.S. Lavorazione Italiana Sughero - Via P.Livornese, 54 - 51011 Buggiano (PT) Italy - Tel. +39.0572/32289 - Fax +39.0572/32083

www.lis.it lis@lis.it www.muffesalnitri.it